

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01M 4/50, 4/52, 10/40	A1	(11) International Publication Number: WO 97/24773 (43) International Publication Date: 10 July 1997 (10.07.97)
---	----	---

(21) International Application Number: PCT/US96/20765

(22) International Filing Date: 16 December 1996 (16.12.96)

(30) Priority Data:
08/579,179 27 December 1995 (27.12.95) US

(71) Applicant: MOTOROLA INC. [US/US]; 1303 East Algonquin Road, Schaumburg, IL 60196 (US).


(72) Inventor: MAO, Zhenhua; 1035 Brookstead Chase, Duluth, GA 30155 (US).

(74) Agents: FULLER, Andrew, S. et al.; Motorola Inc., Intellectual Property Dept., 8000 West Sunrise Boulevard, Fort Lauderdale, FL 33322 (US).

(81) Designated States: CA, CN, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).

Published
With international search report.

(54) Title: ELECTRODE MATERIAL FOR ELECTROCHEMICAL LITHIUM INTERCALATION



7) Abstract

An electrode material for use in a lithium intercalation electrochemical cell. The electrode material is an Li_2NiO_2 material which may be used either alone, or in combination with conventional lithiated transition metal oxide materials. The electrode material provides a reservoir or excess pool of lithium ions adapted to overcome the irreversible capacity loss typically experienced in current lithium ion series.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

ELECTRODE MATERIAL FOR ELECTROCHEMICAL LITHIUM INTERCALATION**Technical Field**

5 This invention relates in general to electrodes and electrode materials for electrochemical cells, and in particular to electrode materials which are adapted to serve as the cathode in lithium intercalation electrochemical cells.

10 Background of the Invention

Numerous transition metal oxide materials have been investigated intensively during the past decade for use as the positive electrode or cathode in a rechargeable lithium ion and lithium polymer batteries. These materials have been investigated because of their gravimetric energy density. Exemplary transition metal oxides include compounds as V₂O₅,
15 V₆O₁₃, TiO₂, MnO₂, LiCoO₂, LiMn₂O₄, and LiNiO₂, to name but a few. Such materials may be combined with negative electrode or anode materials to form electrochemical battery cells. Preferred anode materials depend upon the cathode material selected, and include for example,
20 metallic lithium, lithium alloys, and lithium intercalation materials such as graphite. Alternatively, amorphous carbon based materials such as those disclosed in commonly assigned, copending U.S. Patent Application Serial No. 08/534,427 filed September 27, 1995 disclose novel materials which may be employed as the anode in the cells.

25 Unfortunately, the use of carbon materials as the negative electrode material or anode presents challenges to the designers of electrochemical cells. The initial charge of carbon materials involves formation of electrochemical interfacial films on the carbon particles. This process results in a significant irreversible capacity loss in the cell. Since the charge
30 for this irreversible capacity must come from the positive electrodes, overall capacity of a cell is reduced significantly by the irreversible capacity loss experienced during the first charge and discharge cycle. As an example, if the reversible capacity of a material is approximately 300 mAh/g, but its irreversible capacity loss is 120 mAh/g, then 420 mAh/g, is
35 required to charge one gram of anode material for a usable capacity of 300 mAh. To match the negative capacity, it therefore requires approximately

3.5g. of cathode material for each gram of anode material if the capacity of cathode material is approximately 120 mAh/g.

The need for excess capacity in the cathode so as to overcome the irreversible capacity loss of the anode increases substantially the size, weight, and cost of lithium batteries. Accordingly, it would be desirable if an additional lithium ion source could be put into the positive material and transferred to the anode in order to compensate for the initial irreversible capacity loss. In this way, overall capacity could be significantly improved without deleteriously affecting the size, weight and cost of the cell.

Accordingly, there exists a need for an electrode material which can provide an excess well or reservoir of lithium ions for overcoming the significant irreversible capacity loss experienced by anode materials in lithium intercalation cells. The electrode material must be electrochemically active after the first cycle so as to not degrade the performance of the overall cell into which it is incorporated. Moreover, the electrode material must be composed of materials that are electrochemically stable in the presence of the other components of the cell.

Brief Description of the Drawings

FIG. 1 is a schematic representation of an electrochemical cell including an electrode fabricated of the material disclosed in accordance with the instant patent application;

FIG. 2 is the X-ray diffraction pattern of the electrode material in accordance with the instant invention;

FIG. 3 is the charge and discharge profile of cell voltage for the first ten cycles of an electrochemical cell employing an electrode material in accordance with the instant invention;

FIG. 4 is the charge and discharge profile of an electrochemical cell for the first twenty cycles, employing an electrode material in accordance with the instant invention; and

FIG. 5 is the charge and discharge profiles of an electrochemical cell for the first ten cycles employing an electrode incorporating an electrode material, in accordance with the instant.

Detailed Description of the Preferred Embodiment


While the specification concludes with claims defining the features of the invention that are regarded as novel, it is believed that the invention will be better understood from a consideration of the following description in conjunction with the drawing figures, in which like reference numerals are carried forward.

Referring now to FIG. 1, there is illustrated therein a schematic representation of an electrochemical cell 10 such as a battery or electrochemical capacitor including an electrode having an electrode material in accordance with the instant invention. The electrochemical cell 10 includes a positive electrode or cathode 20 and negative electrode or anode 30, and an electrolyte 40 disposed therebetween. The cell negative electrode or anode 30 is fabricated of a carbon or graphite type material such as that disclosed hereinabove. The cell cathode or positive electrode 20 includes at least the material in accordance with the instant invention, and may further include a lithiated transition metal oxide. The electrolyte 40 disposed between the electrodes may be any of the electrolytes known in the art such as, for example, non aqueous liquid electrolytes such as LiPF_6 , LiClO_4 , LiBF_4 , and combinations thereof. Alternatively, the electrolyte may be a solid electrolyte consisting of a polymeric support structure having an electrolyte active species dispersed therein. In this regard, the electrolyte 40 may be comprised of, for example, polyethylene oxide (PEO) as the polymeric support structure, and lithium salt such as LiClO_4 dispersed therein as the electrolyte active species. In this embodiment, the electrolyte 40 may also act as a separator between the positive and negative electrodes. The electrolyte may also be alternatively an aqueous, non-aqueous, solid-state, gel or some combinations thereof. The electrodes and electrolytes are then enclosed in a package such as a cell case or polymer envelope.

In order to fabricate an electrochemical cell in which the cathode has an excess or a reservoir of lithium ions so as to overcome the irreversible loss experienced by the anode on the first cycle, it is necessary to provide the cathode material with an excess or reservoir of lithium ions. Traditional cathode material such as LiMnO_2 , LiCoO_2 , and LiNiO_2 , do not possess this excess reservoir. Accordingly, the electrode must include a material which does. The cathode 20 should therefore include a

"reservoir" materials such as Li_2NiO_2 or $\text{Li}_4\text{Co}_4\text{O}_6$, each of which have a large initial charge capacity with a reversible capacity comparable to existing materials such as LiCoO_2 and/or LiMn_2O_4 . Accordingly, the cathode material comprises a mix of conventional electrode material such as LiCoO_2 or LiMn_2O_4 , along with Li_2NiO_2 and/or $\text{Li}_4\text{Co}_4\text{O}_6$. In one preferred embodiment of the instant invention, $\text{Li}_4\text{Co}_4\text{O}_6$ and/or Li_2NiO_2 comprises between 10 and 100 wt.% of the cathode, and more preferably between 15 and 35 wt.% of the cathode.

Li_2NiO_2 may be synthesized by high temperature reaction in an inert gas environment. As used herein, inert gas environment refers to helium, nitrogen, and/or argon gas environments. Precursor materials which may be used in the fabrication process include, for example, $\text{Ni}(\text{OH})_2$, Ni powder, or NiO, and LiOH. When $\text{Ni}(\text{OH})_2$ and LiOH are used, the following overall reaction may occur at an elevated temperature, i.e., at temperatures above about 450°C :



Similarly, if NiO and LiOH are used as the starting materials, the following reaction may occur:



Although other nickel and lithium salts may be used as starting materials, the materials described above are preferred since the product is the desired end material. Other salts such as the carbonate or nitrate salts may be used, however, Li_2CO_3 , for example, may be formed. This material would not decompose at temperatures below about 700°C , or alternatively, Ni^{2+} ions may be oxidized to a high valence to form stable phases such as $\text{Li}_2\text{Ni}_8\text{O}_{10}$.

The reaction described above occurs at a reasonable rate at a temperature above about 500°C . Therefore, a reaction temperature higher than 500°C is preferred but should be controlled to less than about 850°C as the product may be decomposed into Li_2O and NiO at higher temperatures. The instant invention may be better understood from the examples which follow.

EXAMPLE

LiOH was mixed with $\text{Ni}(\text{OH})_2$ in a molar ratio of 2.15 to 1, via conventional mixing. The mixture was heated to 450°C in a nitrogen

atmosphere for 12 hours. Thereafter, materials were ground and heated at 650°C in nitrogen atmosphere for approximately 50 hours with two intermittent grinding processes. The final product was dark green and demonstrated the X-ray diffraction pattern (XRD) illustrated in FIG. 2.,
5 when $\text{Cu}\alpha\text{K}_1$ is used as the X-ray source. The XRD analysis plots degrees 2 theta on the abscissa and intensity on the ordinate. Although there is some unreacted NiO and LiOH in the material so fabricated above, the main material Li_2NiO_2 can be defined by the XRD characteristic peaks at the angles as given in FIG. 2. Specifically, the XRD is characterized by a
10 very intense peak at 26 degrees 2 theta, with a secondary peak at about 20 degrees 2 theta.

TEST ONE

The Li_2NiO_2 fabricated in was tested as the positive electrode or
15 cathode material of an electrochemical cell in which the Li_2NiO_2 material comprises essentially 100% of the active material in the cathode. The negative electrode material employed was lithium foil, while the electrolyte was 1M LiPF_6 in 50% ethylene carbonate (EC) and 50% diethylene carbonate (DEC), and a glass mat separator.

20 Referring now to FIG. 3, there is illustrated therein the charge and discharge profiles of an electrochemical cell employing Li_2NiO_2 as the cathode material therein. A perusal of FIG. 3 will show that the initial charge capacity of the Li_2NiO_2 material is 376 mAh/g (line 52), and the discharge capacity is approximately 123 mAh/g (line 54). The initial charge
25 capacity is much larger than in conventional cathode materials, such as LiCoO_2 and LiMn_2O_4 . The material thus possesses the built-in reservoir of Li-ions necessary to overcome dramatic irreversible capacity loss. The discharge capacity is also comparable with conventional LiCoO_2 and LiMn_2O_4 materials. After the first cycle, the charge and discharge curves
30 became nearly symmetric, and remain substantially the same from one cycle to another. Thus, it may be inferred that the capacity of this material is quite stable.

TEST TWO

The Li_2NiO_2 material fabricated as described hereinabove was mixed with conventional LiCoO_2 material to form a positive electrode for an electrochemical cell. The composite electrode comprised 20 wt.% of Li_2NiO_2 and 80 wt.% of LiCoO_2 . Lithium foil was used as the negative electrode in the cell. The electrolyte was as in Test One.

Referring now to FIG. 4, there is illustrated therein the charge and discharge profiles for the electrochemical cell described in this Test Two. The initial charge capacity of this cell was approximately 190 mAh/g (line 56), based on the total positive material versus about 130 mAh/g for conventional LiCoO_2 . Thus, the composite material provides an additional 60 mAh/g capacity on charging. The discharge capacity was approximately 120 mAh/g, (line 58), which is comparable to convention materials. A perusal of FIG. 4 shows that after the first cycle the capacity of the cells was quite stable.

TEST THREE

A composite positive electrode such as that described hereinabove with respect to Test Two was paired with graphite as a negative electrode, and the electrolyte of Test One.

Referring now to FIG. 5, there is illustrated therein the charge and discharge profiles of the electrochemical cell accordingly to this Test Three. FIG. 5 illustrates that for the test cell, a capacity of 120 mAh/g was obtained based upon the total composite positive materials as shown by lines 60 and 62. As may also be appreciated from FIG. 5, the capacity of the cell is quite stable.

While the preferred embodiments of the invention have been illustrated and described, it will be clear that the invention is not so limited. Numerous modifications, changes, variations, substitutions and equivalents will occur to those skilled in the art without departing from the spirit and scope of the present invention as defined by the appended claims.

What is claimed is:

CLAIMS:

1. An electrode for a rechargeable electrochemical cell, said electrode comprising a first electrode material having the formula Li_2NiO_2 , and a second electrode material having the formula LiTMO_2 , wherein TM is one or more transition metal elements selected from the group consisting of Ni, Co, and Mn.
2. An electrode as in claim 1, wherein said first electrode material comprises between 10 and 80 wt.% of the electrode.
3. An electrode as in claim 1, wherein said first electrode material comprises between 15 and 35 wt.% of the electrode.

1/5






FIG. 1


2/5

**FIG. 2**


3/5

**FIG. 3**

4/5

**FIG. 4**

5/5

**FIG. 5**

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US96/20765

A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : H01M 4/50, 4/52, 10/40

US CL : 429/218, 223, 224

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 429/218, 223, 224

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS, STN (CAS ONLINE)

Search terms: Li₂NiO₂, LiNiO₂, LiCoO₂, LiMnO₂, electrode(s), cathode(s)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,429,890 A (PYNENBURG et al.) 04 July 1995, col. 7, lines 55-60.	1-3
X	DAHN et al., Structure and Electrochemistry of Li _{1-x} NiO ₂ and a New Li ₂ NiO ₂ Phase with the Ni(OH) ₂ Structure, Solid State Ionics, 44 (1990) pages 87-97 especially page 93, 2nd column.	1-3
A	US 4,340,652 A (RAISTRICK et al.) 20 July 1982	1-3
A	US 5,378,560 A (TOMIYAMA) 03 January 1995	1-3
A	US 5,478,675 A (NAGAURA) 26 December 1995	1-3

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

Special categories of cited documents:		"T"	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A"	document defining the general state of the art which is not considered to be of particular relevance		
"E"	earlier document published on or after the international filing date	"X"	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L"	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another claim or other special reason (as specified)	"Y"	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O"	document referring to an oral disclosure, use, exhibition or other means		
"P"	document published prior to the international filing date but later than the priority date claimed	"A"	document member of the same patent family

Date of the actual completion of the international search

18 MARCH 1997

Date of mailing of the international search report

04 APR 1997

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

Prince Willis, Jr.
PRINCE WILLIS, JR.

Telephone No. (703) 308-3050

Form PCT/ISA/210 (second sheet)(July 1992)*